Chemicals contained in products

EPSON
EXCEED YOUR VISION

Package-type

Epson Package name; **VFBGA6H-96 / Halogen free**
JEITA Package name; **(P-VFBGA-096-0606-0.50)**
Solder ball Type; **Lead(Pb) Free**
Weight; **0.06** [g] *Note1

Part	Subpart	Subpart weight [mg]	Substance name	CAS No.	Content *Note2 [mg]	Content *Note2 [ppm]	Application
IC Die	IC Die	3.0	Silicon	7440-21-3	3.0	999894	Base material
			Boron	7440-42-8	0.00001	2	Dopant
			Phosphorus	7723-14-0	0.00002	5	Dopant
			Aluminum	7429-90-5	0.0001	20	Metalization
			Arsenic *Note3	7440-38-2	0.00002	5	Dopant
			Fluorine *Note3	7782-41-4	0.00001	2	Dopant
			Titanium *Note3	7440-32-6	0.0001	20	Metalization
			Molybdenum *Note3	7439-98-7	0.0001	20	Metalization
			Tungsten *Note3	7440-33-7	0.0001	30	Metalization
			Cobalt *Note3	7440-48-4	0.00001	2	Metalization
	Stress buffer coat	0.06	Polyimide	-	0.06	1000000	Stress buffer coat *Note4
Package	Substrate	14.7	Glass-cloth	-	2.60	132000	Reinforcement
			Silica	-	0.60	66000	Filler
			Epoxy resin	-	2.90	164300	Base material
			Acrylate resin	-	0.88	85000	Base material
			Pigment	-	0.37	49300	Additive
			Organic filler	-	0.05	3400	Filler
			Arsenic	7440-38-2	0.01	85	Burning resistance
			Chromium compound	-	0.0004	14	Burning resistance
			Copper	7440-50-8	6.10	419901	Copper foil
			Nickel	7440-02-0	0.96	64000	Plating
			Gold	7440-57-5	0.24	16000	Plating
	Die Bonding material	1.03	Epoxy resin	-	0.69	670000	Adhesive
			Acrylic resin	-	0.34	330000	Adhesive
	Solder ball	8.04	Tin	7440-31-5	7.7	957500	Solder ball
			Silver	7440-22-4	0.28	35000	Solder ball
			Copper	7440-50-8	0.060	7500	Solder ball
	Bonding Wire	0.53	Gold	-	0.53	1000000	Conductor
	Mold resin	32.58	Epoxy resin	-	1.60	50000	Base material
			Silica	60676-86-0/-	28.50	873000	Filler
			Carbon black	1333-86-4	0.065	2000	Coloring agent
			Hardening chemical(ex:Phenol resin)	-	1.60	50000	Base material
			Organic phosphorous compound	-	0.16	5000	Hardening accelerator
			Others	-	0.65	20000	Additive

Regarding the information of chemical substances

*Note1 The weight might be somewhat different depending on an individual built-in IC-chip specification like the size etc.
*Note2 Content data are estimated values based on supplier information and intended levels of content in product.
Actual measurements may vary from these values somewhat.
*Note3 Use or not-use of these substances depends on individual built-in IC-chip specification.
*Note4 The stress buffer coat may not be used depending on the individual model.