

Chemicals contained in products

Package-type

Epson Package name; **QFP15-100PIN**

JEITA Package name; **P-LQFP100-1414-0.50**

Lead frame plating; **Lead(Pb) Free**

Weight; **0.69 [g]** *Note1

Part	Subpart	Subpart weight [mg]	Substance name	CAS No.	Content *Note2		Application
					[mg]	[ppm]	
IC Die	IC Die	16	Silicon	7440-21-3	16.2	999894	Base material
			Boron	7440-42-8	0.00003	2	Dopant
			Phosphorus	7723-14-0	0.00008	5	Dopant
			Aluminum	7429-90-5	0.0003	20	Metalization
			Arsenic *Note3	7440-38-2	0.00008	5	Dopant
			Fluorine *Note3	7782-41-4	0.00003	2	Dopant
			Titanium *Note3	7440-32-6	0.0003	20	Metalization
			Molybdenum *Note3	7439-98-7	0.0003	20	Metalization
			Tungsten *Note3	7440-33-7	0.0005	30	Metalization
			Cobalt *Note3	7440-48-4	0.00003	2	Metalization
	Stress buffer coat	0.32	Polyimide	-	0.32	1000000	Stress buffer coat *Note4
Package	Die Bonding material	1.5	Silver	7440-22-4	1.0	640000	Base material
			Epoxy resin	-	0.3	205000	Adhesive
			Phenol resin	-	0.12	80000	Adhesive
			Inorganic powder	-	0.07	48000	Additive
			Bismuth compound	-	0.04	27000	Ion trap
	Lead Frame Plating	12	Tin	7440-31-5	11.8	980000	Solder
			Bismuth	7440-69-9	0.24	20000	Solder
	Lead Frame	152	Copper	7440-50-8	143	945000	Conductor
			Silver	7440-22-4	0.76	5000	Inner lead plating
			Others *Note5	-	7.6	50000	Additive
	Bonding Wire	2.3	Gold	7440-57-5	2.3	1000000	Conductor
	Mold resin	506	Epoxy resin	-	55.7	110000	Base material
			Antimony trioxide	1309-64-4	4.1	8000	Flame retardant
			Halogenated compound(Brominations epoxy)	-	4.1	8000	Flame retardant
			Silica	60676-86-0/-	381	753500	Filler
Carbon black			1333-86-4	5.1	10000	Coloring agent	
Hardening chemical(ex:Phenol resin)			-	55.7	110000	Base material	
			Organic phosphorous compound	-	0.25	500	Hardening accelerator

Regarding the information of chemical substances

*Note1 The weight might be somewhat different depending on an individual built-in IC-chip specification like the size etc.

*Note2 Content data are estimated values based on supplier information and intended levels of content in product.

Actual measurements may vary from these values somewhat.

*Note3 Use or not-use of these substances depends on individual built-in IC-chip specification.

*Note4 The stress buffer coat may not be used depending on the individual model.

*Note5 The nickel, zinc, tin, silicon, iron, and the zinc oxide are included for the Cu type. And the carbon, silicon, and manganese are included for 42alloy type.