

# Chemicals contained in products

## Package-type

Epson Package name; **TQFP14-100PIN / Halogen free**

JEITA Package name; **P-TQFP100-1212-0.40**

Lead frame plating; **Lead(Pb) Free**

Weight; **0.40 [g]** \*Note1

Part	Subpart	Subpart weight [mg]	Substance name	CAS No.	Content *Note2		Application
					[mg]	[ppm]	
IC Die	IC Die	12.5	Silicon	7440-21-3	12.5	999894	Base material
			Boron	7440-42-8	0.00003	2	Dopant
			Phosphorus	7723-14-0	0.00006	5	Dopant
			Aluminum	7429-90-5	0.0003	20	Metalization
			Arsenic *Note3	7440-38-2	0.00006	5	Dopant
			Fluorine *Note3	7782-41-4	0.00003	2	Dopant
			Titanium *Note3	7440-32-6	0.0003	20	Metalization
			Molybdenum *Note3	7439-98-7	0.0003	20	Metalization
			Tungsten *Note3	7440-33-7	0.0004	30	Metalization
			Cobalt *Note3	7440-48-4	0.00003	2	Metalization
	Stress buffer coat	0.25	Polyimide	-	0.25	1000000	Stress buffer coat *Note4
Package	Die Bonding material	0.68	Silver	7440-22-4	0.61	910000	Base material
			Acrylic resin	-	0.05	70000	Adhesive
			Epoxy resin	-	0.01	20000	Adhesive
	Lead Frame Plating	2.36	Tin	7440-31-5	2.36	1000000	Solder
	Lead Frame	154.84	Copper	7440-50-8	146.32	945000	Conductor
			Silver	7440-22-4	0.77	5000	Inner lead plating
			Others *Note5	-	7.74	50000	Additive
	Bonding Wire	1.76	Gold	7440-57-5	1.76	1000000	Conductor
	Mold resin	227.62	Epoxy resin	-	14.34	63000	Base material
			Silica	60676-86-0/-	200.31	880000	Filler
			Carbon black	1333-86-4	0.46	2000	Coloring agent
			Hardening chemical(ex:Phenol resin)	-	9.10	40000	Base material
			Organic phosphorous compound	-	1.14	5000	Hardening accelerator
			others	-	2.28	10000	Additive

Regarding the information of chemical substances

\*Note1 The weight might be somewhat different depending on an individual built-in IC-chip specification like the size etc.

\*Note2 Content data are estimated values based on supplier information and intended levels of content in product.

Actual measurements may vary from these values somewhat.

\*Note3 Use or not-use of these substances depends on individual built-in IC-chip specification.

\*Note4 The stress buffer coat may not be used depending on the individual model.

\*Note5 The nickel, zinc, tin, silicon, iron, and the zinc oxide are included.