

Chemicals contained in products

Package-type

Epson Package name; **QFP8-208PIN-S1**

JEITA Package name; **P-QFP208-2828-0.50**

Terminal plating; **Lead(Pb) Free**

Weight; **5.79 [g]*Note1**

Part	Subpart	Subpart weight [mg]	Substance name	CAS No.	Content *Note2		Application
					[mg]	[ppm]	
IC Die	IC Die	37.8	Silicon	7440-21-3	37.8	999894	Base material
			Boron	7440-42-8	0.000076	2	Dopant
			Phosphorus	7723-14-0	0.00019	5	Dopant
			Aluminum	7429-90-5	0.00076	20	Metalization
			Arsenic *Note3	7440-38-2	0.00019	5	Dopant
			Fluorine *Note3	7782-41-4	0.000076	2	Dopant
			Titanium *Note3	7440-32-6	0.00076	20	Metalization
			Molybdenum *Note3	7439-98-7	0.00076	20	Metalization
			Tungsten *Note3	7440-33-7	0.0011	30	Metalization
	Cobalt *Note3	7440-48-4	0.000076	2	Metalization		
	Stress buffer coat	0.76	Polyimide	-	0.76	1000000	Stress buffer coat *Note4
Package	Die Bonding material	7.5	Silver	7440-22-4	4.8	640000	Base material
			Epoxy resin	-	1.50	205000	Adhesive
			Phenol resin	-	0.60	80000	Adhesive
			Inorganic powder	-	0.36	48000	Additive
			Bismuth compound	-	0.20	27000	Ion trap
	Lead Frame Plating	51.1	Tin	7440-31-5	50.1	980000	Solder
			Bismuth	7440-69-9	1.1	20000	Solder
	Lead Frame	778.4	Copper	7440-50-8	735.6	945000	Conductor
			Silver	7440-22-4	3.9	5000	Inner Lead plating
			Others *Note5	-	38.9	50000	Additive
	Bonding Wire	6.6	Gold	7440-57-5	6.6	1000000	Conductor
	Mold resin	4907.7	Epoxy resin	-	245.4	50000	Base material
			Antimony trioxide	1309-64-4	19.6	4000	Flame retardant
			Halogenated compound(Brominations epoxy)	-	44.2	9000	Flame retardant
			Silica	60676-86-0/-	3960.4	807000	Filler
			Carbon black	1333-86-4	73.7	15000	Coloring agent
			Hardening chemical(ex:Phenol resin)	-	294.4	60000	Base material
Organic phosphorous compound			-	24.6	5000	Hardening accelerator	
others			-	245.4	50000	Additive	

Regarding the information of chemical substances

*Note1 The weight might be somewhat different depending on an individual built-in IC-chip specification like the size etc.

*Note2 Content data are estimated values based on supplier information and intended levels of content in product.

Actual measurements may vary from these values somewhat.

*Note3 Use or not-use of these substances depends on individual built-in IC-chip specification.

*Note4 The stress buffer coat may not be used depending on the individual model.

*Note5 The nickel, zinc, tin, silicon, iron, and the zinc oxide are included for the Cu type. And the carbon, silicon, and manganese are included for 42alloy type.