

Chemicals contained in products

Package-type

Epson Package name; **SQFN7-48PIN / Halogen free**

JEITA Package name; **P-VQFN048-0707-0.50**

Lead frame plating; **Lead(Pb) Free**

Weight; **0.14 [g] *Note1**

| Part | Subpart | Subpart weight [mg] | Substance name | CAS No. | Content ※2 | | Application |
|---------|----------------------|------------------------|-------------------------------------|--------------|--------------|----------|---------------------------|
| | | | | | [mg] | [ppm] | |
| IC Die | IC Die | 4.3 | Silicon | 7440-21-3 | 4.3 | 999894 | Base material |
| | | | Boron | 7440-42-8 | 0.00001 | 2 | Dopant |
| | | | Phosphorus | 7723-14-0 | 0.00002 | 5 | Dopant |
| | | | Aluminum | 7429-90-5 | 0.00009 | 20 | Metalization |
| | | | Arsenic *Note3 | 7440-38-2 | 0.00002 | 5 | Dopant |
| | | | Fluorine *Note3 | 7782-41-4 | 0.00001 | 2 | Dopant |
| | | | Titanium *Note3 | 7440-32-6 | 0.00009 | 20 | Metalization |
| | | | Molybdenum *Note3 | 7439-98-7 | 0.00009 | 20 | Metalization |
| | | | Tungsten *Note3 | 7440-33-7 | 0.00013 | 30 | Metalization |
| | Cobalt *Note3 | 7440-48-4 | 0.00001 | 2 | Metalization | | |
| | Stress buffer coat | 0.09 | Polyimide | - | 0.09 | 1000000 | Stress buffer coat *Note4 |
| Package | Die Bonding material | 0.67 | Silver | 7440-22-4 | 0.61 | 910000 | Base material |
| | | | Acrylic resin | - | 0.05 | 70000 | Adhesive |
| | | | Epoxy resin | - | 0.01 | 20000 | Adhesive |
| | Lead Frame Plating | 0.34 | Tin | 7440-31-5 | 0.3 | 1000000 | Solder |
| | Lead Frame | 56.26 | Copper | 7440-50-8 | 53.17 | 945000 | Conductor |
| | | | Silver | 7440-22-4 | 0.28 | 5000 | Inner lead plating |
| | | | Others *Note5 | - | 2.8 | 50000 | Additive |
| | Bonding Wire | 0.52 | Copper | 7440-50-8 | 0.52 | 1000000 | Conductor |
| | Mold resin | 80.81 | Epoxy resin | - | 5.09 | 63000 | Base material |
| | | | Silica | 60676-86-0/- | 71.11 | 880000 | Filler |
| | | | Carbon black | 1333-86-4 | 0.16 | 2000 | Coloring agent |
| | | | Hardening chemical(ex:Phenol resin) | - | 3.23 | 40000 | Base material |
| | | | Organic phosphorous compound | - | 0.40 | 5000 | Hardening accelerator |
| others | | | - | 0.81 | 10000 | Additive | |

Regarding the information of chemical substances

*Note1 The weight might be somewhat different depending on an individual built-in IC-chip specification like the size etc.

*Note2 Content data are estimated values based on supplier information and intended levels of content in product.

Actual measurements may vary from these values somewhat.

*Note3 Use or not-use of these substances depends on individual built-in IC-chip specification.

*Note4 The stress buffer coat may not be used depending on the individual model.

*Note5 The nickel, zinc, tin, silicon, iron, and the zinc oxide are included.